Production of poly(3-hydroxybutyrate-co-3-hydroxyalkanoate) by recombinant Escherichia coli

<u>박시재</u>, 박종필, 이상엽* 한국과학기술원 생명화학공학과 및 생물공정연구센터 전화 (042) 869-3930, FAX (042) 869-8800

Abstract

Recombinant *E. coli* strains WA101, WB101 and WAB101 harboring p104613C2ReABstb were cultured in LB medium containing sodium decanoate of 2 g/L or sodium decanoate and sodium gluconate of 2 g/L and 10 g/L, respectively, at 30 °C. When sodium decanoate was used as a sole carbon source, all the recombinant *E. coli* strains accumulated poly(3-hydroxybutyrate-co-3-hydroxyalkanoates) [P(3HB-co-3HA)] having various monomer fractions. The mole fraction of 3HB and 3-hydroxyhexanoate (3HHx) in copolymer varied highly depending on the host strains and the kinds of applied mutation. When the *fadB* mutant *E. coli* strains were applied for the production of PHA, the PHA containing high 3HB fraction up to 86 mol% was obtained.

Acknowledgement

This work was supported by the National Research Laboratory Program (2000-N-NL-01-C-237) of the Korean Ministry of Science and Technology (MOST).

References

- 1. Lee SY. "Bacterial polyhydroxyalkanoates" (1996), Biotechno.l Bioeng, 49, 1-14.
- 2. Matsusaki H, Manji S, Taguchi K, Kato M, Fukui T, Doi Y. "Cloning and molecular analysis of the poly(3-hydroxybutyrate) and poly(3-hydroxybutyrate-co-3-hydroxyalkanoate) biosynthesis genes in *Pseudomonas* sp. strain 61-3" (1998), *J. Bacteriol*, 180, 6459-6467.
- 3. Matsusaki H, Abe H, Taguchi K, Fukui T, Doi Y. "Biosynthesis of poly(3-hydroxybutyrate-co-3-hydroxyalkanoates) by recombinant bacteria expressing the PHA synthase gene *phaC1* from *Pseudomonas* sp. 61-3" (2000), *Appl. Microbiol. Biotechnol*, 53, 401-419.
- 4. Tsuge T, Fukui T, Matsusaki H, Taguchi S, Kobayashi G, Ishizaki A, Doi Y. "Molecular cloning of two (R)-specific enoyl-CoA hydratase genes from *Pseudomonas aeruginosa* and their use for polyhydroxyalkanoate synthesis" (2000), *FEMS Microbiol. Lett*, 184, 193-198.




Figure 1. Schematic diagram of p104613C2ReABstb

Table 1. Results of flask cultures of recombinant E. coli strains harboring p104613C2ReABstb^a

Strain	Condition	DCW (g/L)	PHA conc. (g/L)	PHA content (wt%)	Composition			
					3HB	3HHx	3НО	3HD
WA101	b Decanoate	1.90	0.60	31.4	34	63	3	0
	^c Gluconate + Decanoate	3.92	1.90	48.4	89	8	2	1
WB101	Decanoate	1.20	0.30	25.5	86	10	4	0
	Gluconate + Decanoate	3.48	0.88	25.3	87	11	1	1
WAB101	Decanoate	1.25	0.31	25.0	70	26	3	1
	Gluconate + Decanoate	4.15	1.34	32.3	95	2	2	1

^a Cells were cultivated for 72 h in LB medium supplemented with carbon sources as specified in Table.

^b Sodium decanoate was added to the concentration of 2 g/L.

^c Sodium gluconate was added to the concentration of 10 g/L.