

SA05

### The Raman Study of the Uranium Doped Cuprate Based Quasi One-dimensional Antiferromagnet

H. N. Nhat<sup>1\*</sup>, H. D. Chinh<sup>2</sup>, N. Q. Hoa<sup>3</sup>, N. Chau<sup>1</sup> and F. Valach<sup>4</sup>

<sup>1</sup>Center for Materials Science, Vietnam National University, 334-Nguyen Trai, Hanoi, Vietnam

<sup>2</sup>Department of Chemistry, Hanoi University of Technology, 1 Dai Co Viet Str., Hanoi, Vietnam

<sup>3</sup>Department of Physics, Chungbuk National University, Cheongju 361-763, Republic of Korea

<sup>4</sup>Department of Chemical Physics and Nuclear Techniques, Slovak Technical University, Bratislava 812 37, Slovak Republic

\*Corresponding author: namhat@gmail.com, Phone: +84 98 300 6668, Fax: +84 4 768 2007

Recent interests were seen for the uranium doped ceramics because of observed significant improvement in the flux pinning properties of the uranium doped high  $T_c$  superconductors [1]. This paper reports the structure and the Raman scattering study for the cuprate based quasi 1D antiferromagnetic system  $\text{Ca}_2\text{CuO}_2\text{U}$  ( $x=0.05$ ) prepared by the sol-gel method. The samples exhibit the semiconductor character continuously from the room temperature down to the temperature region near 27K where the break from the covalent-insulator state was observed. This turning away from the covalent insulation state has happened for the first time in this class of compounds. We also identified the conduction mechanism in the region above 27K as the possible phonon-assisted electron hopping between the uranium sites in the lattice [2].

#### REFERENCES

- [1] R. Weinstein, US Patent 6083 885 (2000) and R. Weinstein and R. P. Sawh, *Supercond. Sci. Technol.* **15**, 1474 (2002).
- [2] P. Q. Thanh, H. N. Nhat et al., *J. Korean Phys. Soc.* **2007**. In press (accepted).

SA06

### Relation between Mössbauer Spectroscopy and Geometrical Frustration Factors in $\text{MCr}_{1.98}^{57}\text{Fe}_{0.02}\text{O}_4$ ( $M = \text{Co, Zn}$ )

Kang Ryong Choi, Tae Joon Kough, Sam Jin Kim, Chul Sung Kim\*

<sup>1</sup>Department of Physics, Kookmin University, Seoul 136-702, Korea

\*Corresponding author: cskim@phys.kookmin.ac.kr, Phone: +82 2 910 4752, Fax: +82 2 910 5170

In order to elucidate the role of Cr ions in  $\text{MCr}_{1.98}\text{O}_4$  ( $M = \text{Co, Zn}$ ) exhibiting geometrically frustration and multiferroic property [1, 2], we have substituted a small amount of Fe ions for Cr sites and investigated the magnetic behavior of Fe ions using by Mössbauer measurement. The spinel  $\text{MCr}_{1.98}^{57}\text{Fe}_{0.02}\text{O}_4$  powders were prepared by wet chemical solution process. The crystal structure was found to be single-phase cubic spinel with space group of  $Fd\bar{3}m$ . The lattice constants  $a_0$  and the internal structural parameter ( $s$ ) of the oxygen were determined to be 8.340, 8.331 Å and 0.261 and 0.260, respectively. Mössbauer spectra of  $\text{MCr}_{1.98}^{57}\text{Fe}_{0.02}\text{O}_4$  were taken from 4.2 to 295 K using a  $^{57}\text{Co}$  source in a rhodium matrix. The Mössbauer absorption spectra at 4.2K show that the well developed two sextets are superposed with small difference of hyperfine fields ( $H_{\text{hf}}$ ). The hyperfine fields of  $\text{CoCr}_{1.98}^{57}\text{Fe}_{0.02}\text{O}_4$  and  $\text{ZnCr}_{1.98}^{57}\text{Fe}_{0.02}\text{O}_4$  were determined to be 490-480 kOe and 460-450 kOe, respectively. Isomer shift values ( $\delta$ ) of the two sextets are found to be 0.33-0.35 mm/s relative to the Fe metal, which are consistent with the high spin  $\text{Fe}^{3+}$  charge state. From the results of Mössbauer measurement, it is suggested that  $\text{Cr}^{3+}$  ions have two different magnetic sites, and is correlated between hyperfine fields and degree of magnetic frustration.

#### REFERENCES

- [1] S.-H. Lee, C. Broholm, W. Ratcliff, G. Gasparovic, Q. Huang, T. H. Kim, and S.-W. Cheong, *Nature* **418**, 856 (2002).
- [2] Y. Yamasaki, S. Miyasaka, I. Y. Kaneko, J.-P. He, T. Arima, and Y. Tokura, *Phys. Rev. Lett.*, **96**, 207204 (2006).