

Amalgam充填材가 家兔發育齒牙에 미치는 影響에 關한 實驗的 研究

서울大學校 齒科大學

李 正 植

EXPERIMENTAL STUDY OF PULP RESPONSES CAUSED BY AMALGAM RESTORATION ON VITAL RABBITS INCISOR

Chung Sik Lee

College of Dentistry, Seoul National University

I. 緒 言

銀錫 Amalgam이 齒科用材料로서 처음 應用되어 온 것은 1818年 Regnart에 依해서 silver paste로서 紹介되었으나 오늘날과 같은 實用的인 臨床材로 改良된 것은 Black에 의해 비로서 이루어진 것이라 하겠다¹⁻³⁾⁵⁾. 그후 Amalgam充填材가 窩洞內에서의 適合性과 充填操作이 比較的容易해서 頻繁하게 適應됨에 따라 보다優秀한 耐酸性을 갖인 成形充填材를 얻을려고 여러모로 관련을 맺고 研究되었을 뿐 아니라 充填操作의 正確性을期하고자 試圖됨에도 不拘하고 가끔 Amalgam充填施術後에 蓋起될 수 있는 諸缺陷으로 因한 齒髓組織에서의 反應을 檢索코자 多角度에서 많은 索績이 이루어져 umer은 周知의 事實이다. Stock²⁾³⁾는 Amalgam中에 含有되고 있는 水銀成分의 生體에 對한 反應所見을 觀察하였는가 하면 Manley¹⁰⁾, Oman⁵⁾, James and Sihour¹⁶⁾ 및 Sclberkweit et al.¹⁷⁾等은 Amalgam充填施術過程에서 水分에 因한 汚染에서 充填物의 膨脹 및 破切等이 齒質의 汚染의 原因이 됨과 同時に 또한 充填材의 物理學的인 性質의 低下等과 相和로 齒髓組織에서 蓋起된 諸所見을 實驗的으로 追試한 바 齒髓에서의 破壊性變化가 招來된다고 하는가하면 Seeling과 Lefkowitz¹¹⁾

는 이와 反對로 無刺戟性이었다고 하는바 其大部分의 檢索對象을 物理的인 性狀와 臨床病理學의인 所見을 다루어지고 있었다. 이에 著者は 實驗的으로 Amalgam充填을 施術 했을時 特히 全生涯를 通해 持續的으로 齒質形成을 다루는 家兔齒髓組織에 있어서 初期組織變化像을 觀察할 目的으로 醋酸鉛注入에 依한 硬組織 生體染色法을 應用 그 成長鉛線에 依한 形成量의 推移와 더불어 充填後의 反應像을 病理組織學의으로 檢鏡한 바 있어 이를 報告하는 바이다.

II. 實驗材料 및 方法

本實驗에 使用된 動物은 體重 1kg內外의 健康한 家兔 12頭를 實驗 및 對照群에 充填經過日數에 따라 각己 1頭씩 配置하고 實驗的施術은 下顎左右側 中切齒에다 No. 35 inverted cone bur로 五級窩洞을 形成 Zinc Oxide eugenol裹裝을 한 對照群과 無裹裝下에서의 實驗群에 Silver Amalgam充填을 施術하고 곧 이어 0.5%醋酸鉛을 2, 4, 10 및 14日間의 實驗期間中에 각己 2日間隔으로 0.5mg/kg式 耳靜脈注射를 施行한 然後 屠殺 10% formalin液에서 固定 通法에 따라 脫灰 celloidine切片標本을 製作 H-E染色을 하여 檢索하였다. 齒牙硬組織에서의 醋酸鉛生體染色線의 觀察은 舌側象牙質에서 이

투어졌고 测定에 있어서는 micro meter에 依해서 從軸成長速度를 計測하고 이를 齒髓組織에서의 反應所見과 關聯하여 對照檢鏡된 바는 다음과 같다.

III. 實驗成績

充填後 2日經過群에 있어서 對照群에서의 所見은 窩底象牙質에 相當하는 部位에서 象牙芽細胞層은 排列不定과 一部離開된 所見이 觀察되고 또한 Weilis層의 部分의 인消失을 招來케하고 있으나 空胞形成은 觀察되지 않았다. 齒髓組織에서는 中等度의 圓形細胞의 浸潤과 더불어 充血된 組織像으로 觀察되었고 이 境遇의 成長速度는 0.19mm로 計測되었다. 한편 實驗群에 있어서는 象牙芽細胞層에서 空胞變性에 이르는 所見이 発生 齒髓組織에서는 比較的 限局性炎症性變化가 惹起되고 있었다. 이 境遇에 있어서의 平均成長速度는 0.25mm이었다.



圖 1：實驗2日 經過群에 있어서의 齒髓 및 象牙基質

充填 4日 經過群의 對照群에 있어서는 象牙芽細胞層의 部分의 인消失로 排列不定이 招來되고 또한 空胞形成이 惹起되고 있으며 齒髓組織에서도 限局性으로 圓形細胞의 浸潤과 中等度의 充血을 나타내고 있었다. 이 境遇에 있어서의 成長速度는 0.19mm이었다. 實驗群에서는 象牙芽細胞層의 部分의 인消失 또는 萎縮이 形成되고 窩底部에 있어서의 象牙質의 消失等과 齒髓組織에서는 輕度의 弛漫性인 圓形細胞의 浸潤과 充血像等의 炎症性變病이 隨伴되었고 이 境遇에 있어서의 成長速度는 0.21mm로 計測되었다.




圖 2：實驗4日 經過群에 있어서의 齒髓 및 象牙基質

充填 10日 經過群에 있어서는 充填窩洞이 持續的인 發育關係로 對照 및 實驗群 共히 消失되었다. 對照群에서의 所見은 象牙芽細胞層의 萎縮消失 또는 網狀構造가 部分의으로 發見되고 齒冠部齒髓組織에서는 限局性으로 中等度의 圓形細胞의 浸潤 및 充血等이 形成되고 成長速度는 0.17mm로 觀察되었다. 實驗群에 있어서도 亦是 象牙芽細胞層에서의 網狀萎縮된 變性所見이 齒冠部髓腔壁에 沿하여 惹起되고 齒髓組織에 있어서는 弛漫性의 炎症性所見이 이루어 지고 있었다. 이 境遇에 있어서의 成長速度는 0.19mm로 觀察되었다.



圖 3：實驗 10日 經過群에서의 齒冠部象牙質

充填 14日 經過群에 있어서는 兩群 모두 窩洞의 혼적은 認定할 수 없었다. 對照群의 象牙芽細胞層에서의 所見은 거의 10日群의 境遇와 유사하나 間或 齒髓壁가까이 까지 圓形細胞에 遊走되어 있는 所見이 發現되고 充血像은 髓腔壁에 沿하여 認識되고 齒髓中心部에 이르면서

점차消失되어지는所見으로觀察되었고 이境遇에서의成長速度는 0.15mm이었다. 한편對照群에比하여象牙芽細胞層의變性이比較的廣範圍하게髓腔壁에沿하여發見되는느낌이었고 또한齒髓組織에서는充血된彌漫性炎症所見이觀察되고 이境遇의成長速度는 0.17mm로計測되었다.



圖 4: 實驗 14日經過群에서의 齒髓

N. 考 按

充填修復材는齒髓組織에對해서는安定性을부여하여야 할것이나間或窩洞形成時의刺戟과充填材에서의理工學의인刺戟等의諸阻害因子가⁶⁾⁷⁾⁸⁾¹⁰⁾¹²⁾齒髓組織에相互作用하여여러樣相의施術後遺症을惹起시킬수있으나그中에서도특히amalgam shock⁹⁾의現象을考慮Manley⁴⁾, Nachlin¹³⁾, Crawford and Lorson¹⁴⁾및Zander¹⁹⁾는이에齒髓保護手段의必要性을強調한바있으나이와는反對로그와같은阻害因子는窩洞形成時의齒質削除에依한差異와比較觀察할때amalgam充填材는齒髓組織에對해無刺戟性이라하고또Massler¹⁸⁾는amalgam充填時齒髓에對해窩洞이얕은경우別影響이없지만깊을경우에서는炎症性變化를惹起하는경우가적지않다고하고,이경우의因子로는溫熱의인刺戟에서基因된다고한다. Swedlowand Stanley²²⁾는冷水注加下에서五級窩洞形成施術을하고또한乾燥시킨후無裹裝下에서amalgam充填을한경우에서도齒髓組織에亦是限局性的變化가惹起되었다고한다. 그러나Braennstroen²³⁾, 은그의實驗對象38例中22例의所見에서는無反應이라한바있어一致된意見을얻기가어려워本實驗에서는이點을追究코자특히齒髓組織에있어象牙芽細胞의活動에依한齒質形成所見을土臺로한實驗群의結果를一括考察하건대對照群에比하여初期에있어서는成長速度

가比較的많은數值로나타나고施術經過日數가많어짐에따라서점차감약되는傾向이며또한이에따르는齒髓組織에서의反應所見에비추어amalgam充填施術로因한刺戟의防禦機轉에서限局性變病이惹起될것이라하겠다. 그러나이경우의刺戟因子가Seelingand Lefkowitz¹¹⁾¹²⁾의見解와같이窩洞形成時의物理的인因子에서影響이招來된것이라볼수있겠으나窩洞形成이兩對象群에서거의같은條件下에서이루어진것으로본다면Swerdlowand Stanley²²⁾의見解와같이amalgam充填으로惹起된것이라推移할수가있다그러나本實驗에서의齒質形成速度는齒牙從軸方向으로의成長速度만對象으로取扱되것인만큼幅의增加에서오는形成速度에對해서는兩者가恒常一致해서이루어진다고볼수없기때문에考慮치않았음으로앞으로이分野에關聯된追究가더욱이루어져야할것이다.

V. 結 言

著者は實驗動物인家兔前齒에다No.35inverted cone bur로五級窩洞을形成,이에裹裝또는無裹裝下에서의amalgam充填施術을하고2,4,10및14일間의實驗期間中2日間隔으로0.5%醋酸鉛液을注入하여그成長線을計測함과아울러이에따르는齒髓組織에서의所見을檢索하바다음과같은結果를 얻었다.

1)充填施術2日經過群에서는象牙芽細胞層의排列不定및Weilis層의消失이惹起되고이경우의成長速度는0.23mm이었다.

2)充填施術4日經過群에서는象牙芽細胞의一部消失空胞및萎縮된所見이고이경우의成長速度는0.21mm이었다.

3)充填施術10日經過群에서는象牙芽細胞의一部網狀萎縮과齒髓組織에서의充血을隨伴한限局性의炎症所見이觀察되고이에의成長速度는0.19mm이었다.

4)充填施術14日經過群에서는一部彌漫性炎症所見이觀察되는象牙芽細胞에있어서는1.日群과大差없었고이때의成長速度는0.17mm이었다.

參 考 文 獻

- Black: The physical properties of the silver-tin amalgam, Dent. Cosmos, 38, 965, 1896.
- Stock: Die Gefährlichkeit des Quecksilber Dampfes und der Amalgam, med, Klinik, 22, 1709,
- Stock: Die chronische Queck-silber und amalgam Vergiftung, arch, Gerverbepath. U Gewerbehyg, 7, 388, 1936.

- 4) Manley:Apreliminary investigation into the reaction of the pulp to various filling materials, Br, dent, J., 60., 321, 1936
- 5) Sweeney:Delayed expansion in non-zinc alloys J. am dent, ass., 28, 2018, 1941.
- 6) Worner:Excessive expansions in dental amalgams, Aust dent. J., 45, 161, 1941.
- 7) Schoonover:Souder and Beall:Excessive expansion of dental amalgam, J. am. dent. As s., 29, 1825, 1942.
- 8) Liebig and Newark:Excessive expansion of dental amalgams and its relationship to the zinc contents of the alloys. J. dent. Res., 21, 307, 1942.
- 9) Ray:Perspiration ruins amalgam, Dent. Surv 18, 1326, 1942.
- 10) Manley:Investigations into the early effects of various filling materials on the human pulp, Dent, Kec., 62, 1, 1, 1942.
- 11) Seeling and Lefkowitz:pulp response to filling materials, N. Y.dent. J., 16, 540, 1950.
- 12) Van Huysen and Boya:Operative procedure and the tooth. J. prosth, Dent., 3, 818, 1953.
- 13) Nachirw:A type of pain associated with the restoration of teeth with amalgam, J. Am.dent. Ass., 48, 284, 1954.
- 14) Crawford and Lorson:Dental restorative materials. J. dent. Res., 33, 414, 1954.
- 15) Oman:Control of pain in operative dentistry, J.am. dent. Ass., 51, 402, 1955.
- 16) James and Schour:Early dental and pulpal changes following cavity Preparation and filling material in dogs, Oral surg., 8, 1305, 1955.
- 17) Silberkweit Massler, Schour and Weinmann: Effect of filling materials on the pulp of the rat incisor. J. dent. Res., 34, 854, 1955.
- 18) Massler:pulp protection and prevention:Effect of amalgam, Pract dent. Monograph, 29, 1958.
- 19) Zander:Pulp response to restorative materials, J. am. dent. Ass., 59, 911, 1959.
- 20) Ogura, azusawa, mori and mimura:Study of the rate of dentin formation in transverse section of the rabbit's lower incisor. J. dent. Res., 41, 503, 1962.
- 21) Ogura, Uero and mimura:Determination of the rate of longitudinal growth of dentin in the tooth germ of the rabbit. J. dent. Res., 41, 504, 1962.
- 22) Swerdlow and Stanley:Response of the human dental pulp to amalgam restorations, Oral su rg., 15, 499, 1962.
- 23) Braennstroem:Reaction of the pulp to amalgam filling, Odont, Reny. 14, 244, 1963.

<abstract>

Experimental Study of pulp response Caused by Amalgam restoration on vital rabbits incisor

To observe the effect of silver tin amalgam on the pulp tissue and the growth of teeth, the author has prepared class V cavities with #35 inverted cone bur on the lower central incisors of the rabbit, and divided into two groups; the one is control group with zirconia eugenol cement base and the other experimental group without basing.

Silver tin amalgam filling were made on each group, and injected zinc acetate 0.5mg/kg into the auricular vein every other day for 2, 4, 10 and 14 days, and incremental line of dentin and reaction of pulp tissue were observed.

The results were as follow:

1) In the 2day group, it was observed the irregular arrangement of odontoblastic layer and the loss of Weil's layer. The growth rate was 0.23mm average.

2) In the 4day group, it was observed partial loss of odontoblastic layer, vacuolization and reticular formation of odontoblastic layer, and hemorrhage of pulp tissue. The growth rate was 0.21mm average.

3) In the 10day group, it was observed partial reticular formation of odontoblastic layer and inflammatory reaction with hemorrhage of pulp tissue. The growth rate was 0.19mm average.

4) In the 14day group, diffuse inflammatory change was observed on the pulp tissue. The growth rate was 0.17mm average.